



پارس شمیم راه خورشید
تامین کننده مواد اولیه صنایع لاستیک سازی

درباره ما:

شرکت بازرگانی پارس شمیم راه خورشید با هدف تامین نیازهای مشتریان همراه با نوآوری و نیاز سنجی بازار مصرف، از سال ۱۳۹۳ در زمینه واردات مواد اولیه صنایع لاستیک سازی شروع به فعالیت نموده است. این شرکت با بهره گیری از پرسنلی متخصص و مجرب همواره بر آن بوده تا در عرصه رقابتی، با استفاده از به روز ترینهای دنیا، محصولات با قیمت مناسب و کیفیتی عالی و درخور شأن مشتریان گرانقدر فراهم آورد. از جمله محصولات این شرکت می توان کائوچوی طبیعی (SMR20,SVR10) و انواع شتاب دهنده ها (MBTS,TMTD,CBS) و همچنین آنتی اکسیدان ها (IPPD(4010),6PPD(4020),TMQ) با بهترین کیفیت از بهترین کمپانی های دنیا نام برد. امید است با استعانت از الطاف پروردگار بتوانیم گامی هرچند کوچک ، ولی مؤثر در این عرصه برداشته باشیم.

Natural Rubber

SVR-10



Property	Mean test results of Lot No.					Standard (Test Method)
	01	02	03	04	05	
Dirt(Tetained on 44 μ Apererture), (%wt)	0.061	0.062	0.064	0.064	0.069	TCVN 6089:2004 (ISO 249:1995)
Ash, (%wt)	0.030	0.041	0.045	0.046	0.046	TCVN 6087:2010 (ISO 247:206)
Volatile Matter, (%wt)	0.063	0.063	0.065	0.065	0.068	TCVN 6088:2010 (ISO 248:2005)
Nitrogen, (%wt)	0.043	0.047	0.043	0.045	0.041	TCVN 6091:2004 (ISO 1656:1996)
Initial Wallace Plasticity (Po)	46	42	45	45	49	TCVN 6091:2004 (ISO 1656:1996)
PRI (P30 / Po) * 100%	64	68	69	65	69	TCVN 6091:2004 (ISO 1656:1996)





SMR-20



Property	SMR 20 Limit
Dirt(Retained on 44 μ Aperture), (%wt)	0.16
Ash, (%wt)	1.00
Volatile Matter, (%wt)	0.80
Nitrogen, (%wt)	0.60
Initial Wallace Plasticity (po) Range Average	po \geq 30
PRI (P_{30} / P_o) \times 100%	\geq 40

Accelerator

ITEMS	STANDARD
Appearance	Gray-White / Light-Yellow Powder / Granule
Melting Point °C	≥ 97.0
Heating Loss %	≤ 0.50
Ash Content %	≤ 0.40
Sieve Residue (100 mesh) %	≤ 0.10
Insoluble In Methanol %	≤ 0.80
Purity %	≥ 95.0



CBS 



TMTD



ITEMS	STANDARD
Appearance	White to Off-White Powder
Assay %	≥ 96
Initial Melting Point °C	≥ 140
Heating Loss %	≤ 0.30
Ash Content %	≤ 0.30
Residue On 63 μm Sieve %	≤ 0.50
Residue On 150 μm Sieve %	≤ 0.10



MBTS



ITEMS	STANDARD
Appearance	Gray-white / Light-Yellow Powder / Granule
Melting Point °C	≥ 164.0
Heating Loss %	≤ 0.40
Ash Content %	≤ 0.50
Sieve Residue (100 Mesh) %	≤ 0.10 (Powder Grade)
Purity %	≥ 95.0

Antioxidant

ITEMS	STANDARD
Appearance	Amber to brown pastilles
Total Content Of Dimer, Trimer And Tetramer %	≥ 50.0
Isopropyl Bis Aniline Content %	≥ 0.50
Soften Point °C	80.0 - 100.0
Insoluble In Ethanol %	≤ 0.20
Heating Loss (50-55°C) %	≤ 0.50
Ash Content %	≤ 0.50



TMQ





6PPD(4020)



ITEMS	STANDARD
Appearance	Blackish Brown Pastilles
Purity %	≥ 95.0
Melting Point (Initial) °C	≥ 45.0
Solidifying Point °C	≥ 44.0
Heating Loss %	≤ 0.50
Ash Content %	≤ 0.30



IPPD(4010)



ITEMS	STANDARD
Appearance	Purple to greyish brown flakes or granule
Purity %	≥ 92.0
Melting point °C	≤ 70.0
Heating loss %	≤ 0.50
Ash content %	≤ 0.30



تماس با ما:

+98 21 66716065

info@parskhorshid.com

www.parskhorshid.com

Parskhorshid.group



فروش پایان یک معامله نیست، آغاز یک تعهد است